

Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11) **EP 0 799 843 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention  
of the grant of the patent:  
**04.06.2003 Bulletin 2003/23**

(51) Int Cl.<sup>7</sup>: **C08G 18/79**

(21) Application number: **97104707.1**

(22) Date of filing: **19.03.1997**

(54) **Polyurethane resins containing carbodiimide bonds**

Carbodiimide enthaltende Polyurethanharze

Résines polyuréthane contenant des groupes carbodiimides

(84) Designated Contracting States:  
**DE FR GB**

(30) Priority: **02.04.1996 JP 10459996**

(43) Date of publication of application:  
**08.10.1997 Bulletin 1997/41**

(73) Proprietor: **NISSHINBO INDUSTRIES, INC.**  
**Chuo-ku, Tokyo 103 (JP)**

(72) Inventors:  
• **Imashiro, Yasuo, c/o Nisshinbo Ind. Inc. Tokyo**  
**Adachi-ku, Tokyo 123 (JP)**

- **Takahashi, Ikuo, c/o Nisshinbo Ind. Inc. Tokyo**  
**Adachi-ku, Tokyo 123 (JP)**
- **Horie, Naofumi, c/o Nisshinbo Ind. Inc. Tokyo**  
**Adachi-ku, Tokyo 123 (JP)**
- **Yamane, Takeshi, c/o Nisshinbo Ind. Inc. Tokyo**  
**Adachi-ku, Tokyo 123 (JP)**

(74) Representative: **Laufhütte, Dieter, Dr.-Ing. et al**  
**Lorenz-Seidler-Gossel**  
**Widenmayerstrasse 23**  
**80538 München (DE)**

(56) References cited:  
**EP-A- 0 460 481** **EP-A- 0 527 371**  
**FR-A- 2 311 806** **US-A- 5 357 021**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

## Description

### Background of the Invention

#### 1. Field of the Invention

[0001] The present invention relates to a novel polyurethane resin. More particularly, the present invention relates to a polyurethane resin which contains carbodiimide groups in the molecular chain and which shows water resistance stably over a long period of time.

#### 2. Prior Art

[0002] Polyurethane resins have high elasticity and are in use in various applications such as molded product, thread, coating film, etc. Meanwhile, they are inferior in chemical resistance, heat resistance and water resistance and, therefore, have not been used in the applications where said properties are required, such as hose and packing for automobile engine and peripherals.

[0003] Of various polyurethane resins, polyester polyurethane resins obtained from a polyester polyol contain a large number of ester bonds in the molecule and, when used under high-temperature and high-humidity conditions, give rise to hydrolysis of ester bonds and consequent molecular weight reduction, inviting deterioration of strength and elastic modulus.

[0004] In order to alleviate the above-mentioned problems of polyurethane resin caused by ester bond hydrolysis and consequent molecular weight reduction, it has heretofore been proposed to add an additive to a polyurethane resin. An example of such proposals is to add epoxy, oxazoline, carbodiimide or the like to a polyurethane resin to allow the additive to trap the carboxyl group formed by hydrolysis of the polyurethane resin and extend the life of the polyurethane resin.

[0005] However, since the additive is simply added to a polyurethane resin, the additive bleeds out onto the surface of the polyurethane resin; when the additive is added to a polyurethane resin which comes into contact with a solvent or an oil, the additive is extracted by the solvent or oil, inviting the performance deterioration of the solvent or oil and the reduction in hydrolysis resistance of the polyurethane resin. Therefore, the effect of addition of the above additive to polyurethane resin as a hydrolysis resistant is not fully satisfactory.

[0006] Moreover, since the above additive is generally a powdery solid of high melting point, dispersion thereof in polyurethane resin needs a very complicated apparatus and a fairly long time.

### Object and Summary of the Invention

[0007] The object of the present invention is to eliminate the above-mentioned drawbacks of the prior art and provide a polyurethane resin containing carbodiimide bonds in the molecular chain, which exhibits hydrolysis resistance stably over a long period of time without losing the carbodiimide bonds out of the molecule and which has improved heat resistance.

[0008] According to the present invention, there is provided a polyurethane resin obtained from a diol component and a diisocyanate component by an ordinary process, wherein the diisocyanate component comprises:

at least one kind of unmodified diisocyanate, and

at least one kind of carbodiimide-modified aromatic diisocyanate having, at one or both of the ortho positions of the two isocyanate groups, an aliphatic, alicyclic or aromatic substituent of one or more carbon atoms, and the molar ratio of the unmodified diisocyanate and the carbodiimide-modified aromatic diisocyanate is 35-0.1:1.

[0009] According to the present invention, there is also provided a polyurethane resin obtained from a diol component and a diisocyanate component by an ordinary process, wherein the diisocyanate component comprises:

at least one kind of unmodified diisocyanate, and

at least one kind of carbodiimide-modified aliphatic diisocyanate wherein at least one of the two carbons each bonded with an isocyanate group is di- or tri-substituted, and the molar ratio of the unmodified diisocyanate and the carbodiimide-modified aliphatic diisocyanate is 35-0.1:1.

### Detailed Description of the Invention

[0010] The present invention is hereinafter described in detail.


[0011] As mentioned above, the polyurethane resin of the present invention is obtained from a diol component and a diisocyanate component by an ordinary process. The diol component as the first component of the polyurethane resin can be any diol as long as it has conventionally been used in production of polyurethane resin. The diol can be exemplified by saturated or unsaturated low-molecular glycols such as ethylene glycol, 1,2-propanediol, 1,3-propanediol, 1,4-butanediol, neopentyl glycol, pentanediol, hexanediol, octanediol, 1,4-butenediol, diethylene glycol, triethylene glycol, dipropylene glycol and the like; alkyl glycidyl ethers such as n-butyl glycidyl ether, 2-ethylhexyl glycidyl ether and the like; polyester polyols obtained by subjecting, to dehydration and condensation, a monocarboxylic acid-glycidyl alcohol ester (e.g. versatic acid-glycidyl alcohol ester) and a dibasic acid or an anhydride thereof (e.g. adipic acid, phthalic acid, isophthalic acid, terephthalic acid, maleic acid, fumaric acid, succinic acid, oxalic acid, malonic acid, glutaric acid, pimelic acid, suberic acid, azelaic acid, sebacic acid or dimer acid); and polyester polyols obtained by subjecting a cyclic ester compound to ring-opening polymerization.

[0012] The polyurethane resin of the present invention is not different from conventional urethane resins in that it is composed of a diol component and a diisocyanate component. However, the present polyurethane resin is characterized in that the diisocyanate component as the second component of the resin comprises at least one kind of unmodified diisocyanate and at least one kind of carbodiimide-modified diisocyanate.


[0013] In Japanese Patent Application Laid-Open No. 5-302050 is disclosed a printing ink using a urethane resin composition composed of a polyol, a carbodiimide-modified diisocyanate, a chain extender, etc. The urethane resin described in the literature, however, uses, as the isocyanate component, only a carbodiimide-modified diisocyanate and, therefore, is low in elastic modulus as shown in Comparative Examples described later and has no satisfactory properties for use as general elastomer, molding material, artificial leather, sealing agent or film.

[0014] The unmodified diisocyanate, which is one of the second component of the present polyurethane resin, can be any unmodified diisocyanate as long as it has conventionally been used in production of polyurethane resin. The unmodified diisocyanate can be exemplified by 1,5-naphthylene diisocyanate, 4,4'-diphenylmethane diisocyanate, 4,4'-diphenyldimethylmethane diisocyanate, 4,4'-dibenzyl diisocyanate, dialkyldiphenylmethane diisocyanate, 1,3-phenylene diisocyanate, 1,4-phenylene diisocyanate, tolylene diisocyanate, butane-1,4-diisocyanate, hexamethylene diisocyanate, isopropylene diisocyanate, naphthylene diisocyanate, methylene diisocyanate, 2,2,4-trimethylhexamethylene diisocyanate, cyclohexane-1,4-diisocyanate, xylylene diisocyanate, hydrogenated xylylene diisocyanate, isophorone diisocyanate, lysine diisocyanate, dicyclohexylmethane-4,4'-diisocyanate, 1,3-bis(isocyanatomethyl)cyclohexane, methylcyclohexane diisocyanate, m-tetramethylxylylene diisocyanate, 2,4,6-triisopropylbenzene diisocyanate, isopropylidene bis(4-cyclohexylisocyanate) and tolidine diisocyanate.


[0015] The carbodiimide-modified diisocyanate, which is the other of the second component of the present polyurethane resin, includes a carbodiimide-modified aromatic diisocyanate of high steric hindrance having, at one or both of the ortho positions of the two isocyanate groups, an aliphatic, alicyclic or aromatic substituent of one or more carbon atoms. Specific examples of such a carbodiimide-modified aromatic diisocyanate are those derived from a diisocyanate selected from the group consisting of 2,4,6-triisopropylbenzene diisocyanate represented by the following formula:




diethyltolylene diisocyanate represented by the following formulas:




(either one or a mixture of the two) and 3,3'-ethyl-5,5'-methyl-4,4'-diphenylmethane diisocyanate represented by the following formula:




[0016] The carbodiimide-modified diisocyanate, which is the other of the second component of the present polyurethane resin, also includes a carbodiimide-modified aliphatic diisocyanate wherein at least one of the two carbons each bonded with an isocyanate group is di- or tri-substituted. Specific examples of such a carbodiimide-modified aliphatic diisocyanate are those derived from a diisocyanate selected from the group consisting of 4,4'-dicyclohexylmethane diisocyanate represented by the following formula:




tetramethylxylene diisocyanate represented by the following formula:



and isophorone diisocyanate represented by the following formula:



[0017] The above-mentioned diisocyanates may be used singly or in admixture of two or more compounds. However, when there is used an aromatic diisocyanate of low steric hindrance or an aliphatic diisocyanate wherein the carbon (s) bonded with an isocyanate group is mono-substituted or is not substituted, for example, 4,4'-diphenylmethane diisocyanate represented by the following formula:



or hexamethylene diisocyanate represented by  $\text{OCN}-(\text{CH}_2)_6-\text{NCO}$ , it is impossible to obtain a carbodiimide-modified diisocyanate usable in the present invention, because crosslinking between carbodiimide groups or uretone-imine crosslinking between carbodiimide and isocyanate takes place, inviting thickening and solidification.

[0018] The carbodiimide-modified diisocyanate can be synthesized from the above-mentioned diisocyanate by a reaction using a carbodiimidization catalyst.

[0019] The carbodiimidization catalyst is preferably an organic phosphorus type compound, particularly preferably phospholene oxide in view of the activity. Specific examples thereof are 3-methyl-1-phenyl-2-phospholene-1-oxide, 3-methyl-1-ethyl-2-phospholene-1-oxide, 1,3-dimethyl-2-phospholene-1-oxide, 1-phenyl-2-phospholene-1-oxide, 1-ethyl-2-phospholene-1-oxide, 1-methyl-2-phospholene-1-oxide and double bond isomers thereof. Of these, 3-methyl-1-phenyl-2-phospholene-1-oxide, which is commercially available, is particularly preferred.

[0020] The carbodiimide-modified diisocyanate can be produced by a known process. It can be produced, for example, by adding, to the above-mentioned diisocyanate, the above-mentioned catalyst in an amount of 0.1-10% by weight (a larger amount is possible when the economy is neglected), preferably 0.5-5% by weight based on the diisocyanate, in the presence or absence of a solvent inert to the isocyanate, in an inert gas (e.g. nitrogen) current or with the inert gas bubbled through the solvent, and stirring the mixture at 120-200°C to give rise to carbon dioxide elimination and condensation.

[0021] The rate of the carbodiimidization varies depending upon the kind of the diisocyanate used, and too high a rate makes it difficult to control the polymerization degree. Therefore, it is preferable to allow the reaction to proceed at an appropriate catalyst amount and at an appropriate reaction temperature. For example, in carbodiimide-modifying an aliphatic diisocyanate, the catalyst amount can be 0.1-10% by weight, preferably 0.5-5% by weight and the reaction temperature can be 120-200°C; and in carbodiimide-modifying an aromatic diisocyanate, the catalyst amount can be 0.01-5% by weight, preferably 0.05-1% by weight and the reaction temperature can be 50-180°C.

[0022] The thus-produced carbodiimide-modified diisocyanate has preferably 1-20, more preferably 1-15 carbodiimide groups because such a carbodiimide-modified diisocyanate has a low melting point and a low viscosity and can be easily dispersed in or mixed with other materials for polyurethane resin.

[0023] The polyurethane resin of the present invention can be produced by reacting the above-mentioned diol component and the above-mentioned diisocyanate component comprising at least one kind of unmodified diisocyanate and at least one kind of carbodiimide-modified diisocyanate, according to an ordinary process.

[0024] The above urethanization is conducted at 20-200°C, preferably at 60-150°C. Since this urethanization is an exothermic reaction, it is difficult to control the reaction temperature strictly. However, when the reaction temperature is too low, the reaction rate is small and a long time is required; when the reaction temperature is too high, the reaction rate is too large and insufficient mixing occurs, inviting nonuniform reaction and deterioration (burning) of polyurethane resin formed.

[0025] When the urethanization rate is small, it is possible to use an ordinary urethanization catalyst, for example,

an amine (e.g. triethylenediamine) or an organotin (e.g. dibutyltin dilaurate) in an amount of 0.001-1% by weight based on the polyurethane resin formed. It is also possible to use, at the time of synthesis, at least one kind of solvent such as dimethylformamide (DMF), tetrahydrofuran (THF), methyl ethyl ketone (MEK), toluene or the like.

[0026] It is also possible to (1) react a diol component with a diisocyanate component to synthesize an isocyanate group-terminated prepolymer, and add, to the prepolymer, a chain extender consisting of a diol (e.g. butanediol, ethylene glycol or propylene glycol) or a diamine (e.g. ethylenediamine, propylenediamine, triethylenediamine, butylenediamine or hexylenediamine), or (2) react a diol component with an unmodified diisocyanate to synthesize a hydroxyl group-terminated prepolymer, and add a carbodiimide-modified diisocyanate to the prepolymer, or (3) react a diol component with an unmodified diisocyanate to synthesize a hydroxyl group-terminated prepolymer, react the prepolymer with a carbodiimide-modified diisocyanate, and add a chain extender to the reaction product.

[0027] It is also possible to (1) react a diol component with a carbodiimide-modified diisocyanate to synthesize a hydroxyl group-terminated prepolymer, and react the prepolymer with an unmodified diisocyanate, or (2) react a diol component with a carbodiimide-modified diisocyanate to synthesize a hydroxyl group-terminated prepolymer, react the prepolymer with an unmodified diisocyanate to synthesize an isocyanate group-terminated prepolymer, and add a chain extender to the prepolymer, or (3) react a diol component with a carbodiimide-modified diisocyanate and a diol component with an unmodified diisocyanate to synthesize a hydroxyl group-terminated prepolymer and an isocyanate group-terminated prepolymer, and mixing the two prepolymers, or (4) react a diol component with a carbodiimide-modified diisocyanate and a diol component with an unmodified diisocyanate to synthesize a hydroxyl group-terminated prepolymer and an isocyanate group-terminated prepolymer, mixing the two prepolymers, and add a chain extender to the mixture.

[0028] It is also possible to add, to a carbodiimide-modified diisocyanate or an isocyanate group-terminated prepolymer, a known isocyanate-blocking agent such as phenol (e.g. phenol or xylenol), aliphatic alcohol (e.g. methanol, ethanol, isopropanol or cyclohexyl alcohol), oxime (e.g. methyl ethyl ketoxime), amine, amide, imide, lactam (e.g.  $\epsilon$ -caprolactam), dicarbonyl compound (e.g. diethyl malonate or ethyl acetoacetate) or the like to block the isocyanate group, and heating the resulting product with a hydroxyl group-terminated prepolymer and a chain extender (e.g. bifunctional or higher alcohol or amine) to regenerate the isocyanate, and react with hydroxyl group to synthesize a polyurethane.

[0029] In the above reaction, it is possible to add an appropriate amount of a carbodiimidization catalyst to the urethanization system to convert part of the isocyanate groups remaining in the system into carbodiimide groups and thereby introduce carbodiimide bonds into the molecule of the polyurethane resin formed.

[0030] In the above reaction, the amount of the carbodiimidization catalyst differs depending upon the isocyanate group content in the material to be reacted, the kind and amount of the urethanization catalyst used, and the urethanization temperature employed.

[0031] In the present polyurethane resin produced as above, the molar ratio of the unmodified diisocyanate and the carbodiimide-modified diisocyanate can be, for example, 35-0.1:1, preferably 10-0.5:1. When the content of the unmodified diisocyanate is more than the upper limit, the resulting polyurethane resin has low hydrolysis resistance; and when the content is less than the lower limit, it is impossible to obtain a polyurethane resin of high elasticity.

[0032] In the present polyurethane resin, the content of carbodiimide groups possessed by at least one kind of carbodiimide-modified diisocyanate is preferably  $1 \times 10^{-2}$  to  $1 \times 10^{-6}$  mole, more preferably  $1 \times 10^{-3}$  to  $1 \times 10^{-5}$  mole per g of the polyurethane resin. When the content of carbodiimide groups is lower than the lower limit, the resulting polyurethane resin has low hydrolysis resistance; and when the content of carbodiimide groups is higher than the upper limit, the resulting polyurethane resin has too low elasticity, making it impossible to obtain a satisfactory polyurethane resin.

[0033] In the present polyurethane resin, the molecular weight can be, for example, 5,000-200,000 and the index (NCO/OH) can be, for example, 0.8-1.5, preferably 1.0-1.1.

[0034] The present polyurethane resin is obtained as a substance which is solid at atmospheric temperature, when no solvent is used in the production. Therefore, it can be used in a solution form after being dissolved in a solvent, or as a powder form after being ground; or, can be molded or spun by the use of an extruder or an injection molding machine at 150-250°C, preferably at 170-200°C to obtain a product. Needless to say, it is possible to introduce a polyurethane resin before solidification into an extruder or the like, wherein melt kneading is conducted to complete urethanization.

[0035] During the production of the present polyurethane resin, it is possible to add, with no problem, known additives such as oxidation inhibitor, ultraviolet absorber, light stabilizer and the like.

[0036] The present invention is hereinafter described in more detail by way of Examples.

[Synthesis of carbodiimide-modified diisocyanates]

<Synthesis Example 1>

5 [0037] In a 500-ml separable flask equipped with a condenser tube were placed 200 g of 4,4'-dicyclohexylmethane diisocyanate and 1 g of 3-methyl-1-phenyl-2-phospholene-1-oxide. They were stirred by the use of a mechanical stirrer in a nitrogen current at 185°C for 3 hours to obtain a carbodiimide-modified diisocyanate having an average molecular weight of 480 and an average polymerization degree of  $n=1$ .

10 <Synthesis Examples 2 to 36>

[0038] Carbodiimide-modified diisocyanates shown in Table 1 were obtained by conducting the same operation as in Synthesis Example 1 except that the reaction time and the diisocyanate were changed. Incidentally, in Synthesis Examples 19-36, the catalyst amount was 0.3%.

Table 1

No. of Synthesis Example	Diisocyanate used	Average degree of polymerization
1	HMDI	1
2	HMDI	3
3	HMDI	5
4	HMDI	7
5	HMDI	10
6	HMDI	15
7	IPDI	1
8	IPDI	3
9	IPDI	5
10	IPDI	7
11	IPDI	10
12	IPDI	15
13	TMXDI	1
14	TMXDI	3
15	TMXDI	5
16	TMXDI	7
17	TMXDI	10
18	TMXDI	15
19	E,M-MDI	1
20	E,M-MDI	3
21	E,M-MDI	5
22	E,M-MDI	7
23	E,M-MDI	10
24	E,M-MDI	15
25	E-TDI	1
26	E-TDI	3
27	E-TDI	5

Table 1 (continued)

No. of Synthesis Example	Diisocyanate used	Average degree of polymerization
28	E-TDI	7
29	E-TDI	10
30	E-TDI	15
31	TIDI	1
32	TIDI	3
33	TIDI	5
34	TIDI	7
35	TIDI	10
36	TIDI	15
In Table 1, the diisocyanates shown are as follows. HMDI: 4,4'-dicyclohexylmethane diisocyanate IPDI: isophorone diisocyanate TMXDI: tetramethylxylene diisocyanate E,M-MDI: 3,3-ethyl-5,5'-methyl-4,4'-diphenylmethane diisocyanate E-TDI: diethyltolylene diisocyanate TIDI: 2,4,6-triisopropylbenzene diisocyanate		

[Synthesis of polyurethane resins]

<Examples 1A to 36B>

**[0039]** To 2,113 g of a polyester polyol having an average molecular weight of 2,113 composed of adipic acid/ethylene glycol/propylene glycol were added 4,4'-diphenylmethane diisocyanate and one of the carbodiimide-modified diisocyanates obtained in Synthesis Examples 1-36, in respective amounts shown in Tables 2. Each mixture was subjected to a reaction at 80°C for 5 hours to obtain various prepolymers. One of the prepolymers and 200 g of butane diol were reacted by the use of a melt extrusion reactor; the resulting polyurethane was extruded at a final temperature of 185°C by the use of a T-die having a thickness of 250 µm to obtain various films; and each film was wound up by a winder.

Table 2

Example	Diisocyanates	A	B	C	D	E
	MDI	821	721	596	423	346
1	Syn. Ex. 1	48	240	480	812	960
2	Syn. Ex. 2	92	458	916	1550	----
3	Syn. Ex. 3	135	676	1352	2288	----
4	Syn. Ex. 4	279	894	1788	----	----
5	Syn. Ex. 5	244	1221	2442	----	----
6	Syn. Ex. 6	353	1766	----	----	----
7	Syn. Ex. 7	44	222	444	751	888
8	Syn. Ex. 8	84	422	844	1428	1688
9	Syn. Ex. 9	124	622	1244	----	----
10	Syn. Ex. 10	162	822	1644	----	----
11	Syn. Ex. 11	244	1122	2244	----	----
12	Syn. Ex. 12	224	1622	----	----	----



Table 2 (continued)

Example	Diisocyanates	A	B	C	D	E
	MDI	821	721	596	423	346
13	Syn. Ex. 13	40	200	400	677	800
14	Syn. Ex. 14	76	379	757	1281	1514
15	Syn. Ex. 15	111	557	1113	----	----
16	Syn. Ex. 16	147	735	1470	----	----
17	Syn. Ex. 17	201	1003	2005	----	----
18	Syn. Ex. 18	290	1448	----	----	----
19	Syn. Ex. 19	75	374	748	1266	1496
20	Syn. Ex. 20	145	726	1452	----	----
21	Syn. Ex. 21	216	1078	----	----	----
22	Syn. Ex. 22	286	1430	----	----	----
23	Syn. Ex. 23	392	----	----	----	----
24	Syn. Ex. 24	568	----	----	----	----
25	Syn. Ex. 25	42	210	420	711	840
26	Syn. Ex. 26	80	398	796	1347	1592
27	Syn. Ex. 27	177	586	1172	----	----
28	Syn. Ex. 28	155	774	1548	----	----
29	Syn. Ex. 29	211	1056	2112	----	----
30	Syn. Ex. 30	305	1526	----	----	----
31	Syn. Ex. 31	53	266	532	900	1064
32	Syn. EX. 32	102	510	1020	1725	----
33	Syn. Ex. 33	151	754	1508	----	----
34	Syn. Ex. 34	200	998	1996	----	----
35	Syn. Ex. 35	273	1364	----	----	----
36	Syn. Rx. 36	395	1974	----	----	----

[0040] In Tables 2-4, MDI refers to 4,4'-diphenylmethane diisocyanate; and Example 1A, for example, indicates that in the column A of Table 2, there were used 821 g of 4,4'-diphenylmethane diisocyanate and 48 g of the carbodiimide-modified diisocyanate of Synthesis Example 1.

#### <Comparative Example 1>

[0041] To 2,113 g of a polyester polyol having an average molecular weight of 2,113 composed of adipic acid/ethylene glycol/propylene glycol was added 846 g of 4,4'-diphenylmethane diisocyanate. The mixture was subjected to a reaction at 80°C for 5 hours to obtain a prepolymer. The prepolymer and 200 g of butane diol were reacted by the use of a melt extrusion reactor; the resulting polyurethane was extruded at a final temperature of 185°C by the use of a T-die having a thickness of 250 µm to obtain a film; and the film was wound up by a winder.

#### [Hydrolysis test]

[0042] Each of the polyurethane films obtained in Examples 1A to 36B and Comparative Example 1 was subjected to punching to obtain a test piece of dumbbell shape. Each test piece was immersed in water of 95°C, taken out in the 15th day, and measured for tensile strength retention (%). The results are shown in Table 3. Incidentally, the polyurethane film of Comparative Example 1 broke.

Table 3

Example	A	B	C	D	E
1	58	60	63	70	75
2	59	62	65	73	77
3	62	67	69	72	-
4	65	68	70	-	-
5	68	72	75	-	-
6	72	74	-	-	-
7	43	47	52	60	63
8	45	49	54	62	68
9	52	49	56	-	-
10	60	62	64	-	-
11	62	55	67	-	-
12	65	68	-	-	-
13	72	74	78	80	82
14	72	75	80	83	85
15	74	77	82	-	-
16	76	79	86	-	-
17	79	80	86	-	-
18	82	85	-	-	-
19	36	42	45	49	56
20	39	44	48	-	-
21	43	47	-	-	-
22	47	50	-	-	-
23	52	-	-	-	-
24	59	-	-	-	-
25	40	44	46	49	52
26	43	47	49	54	57
27	47	50	56	-	-
28	52	54	62	-	-
29	56	58	65	-	-
30	59	64	-	-	-
31	60	62	65	64	70
32	63	64	67	68	-
33	65	67	69	-	-
34	69	70	72	-	-
35	72	74	-	-	-
36	74	79	-	-	-

[Synthesis of polyurethane resins]

<Comparative Examples 2-10>

[0043] To 2,113 g of a polyester polyol having an average molecular weight of 2,113 composed of adipic acid/ethylene glycol/propylene glycol was added a carbodiimide-modified diisocyanate shown in Table 4, in an amount shown in Table 4. The mixture was subjected to a reaction at 80°C for 5 hours to obtain a prepolymer. The prepolymer and 200 g of butane diol were reacted by the use of a melt extrusion reactor; and the resulting polyurethane was extruded at a final temperature of 185°C by the use of a T-die having a thickness of 250 µm. However, each polyurethane obtained had low elasticity and could not be extruded into a film shape.

Table 4

Comparative Example	Carbodiimide-modified diisocyanate		
	Diisocyanate used	Average polymerization degree	Amount used
2	HMDI	3	3100
3	HMDI	5	4575
4	HMDI	10	8264
5	IPDI	3	2562
6	IPDI	5	3766
7	IPDI	10	6785
8	TMXDI	3	2856
9	TMXDI	5	4210
10	TMXDI	10	7594
11	TIDI	3	4914
12	TIDI	5	7296
13	TIDI	10	13252
14	E,M-MDI	3	2694
15	E,M-MDI	5	3966
16	E,M-MDI	10	7147
17	E-TDI	3	3452
18	E-TDI	5	5103
19	E-TDI	10	9232

[0044] As is clear from the above, the present invention *provides* a polyurethane resin having carbodiimide bonds in the molecular chain, which exhibits water resistance stably over a long period of time.

#### Claims

1. A polyurethane resin obtained from a diol component and a diisocyanate component by an ordinary process, wherein the diisocyanate component comprises:

at least one kind of unmodified diisocyanate, and  
at least one kind of carbodiimide-modified aromatic diisocyanate having, at one or both of the ortho positions of the two isocyanate groups, an aliphatic, alicyclic or aromatic substituent of one or more carbon atoms,

and the molar ratio of the unmodified diisocyanate and the carbodiimide-modified aromatic diisocyanate is 35-0.1:1.

2. A polyurethane resin according to Claim 1, wherein the carbodiimide-modified aromatic diisocyanate is derived from a diisocyanate selected from the group consisting of 2,4,6-triisopropylbenzene diisocyanate, diethyltolylene diisocyanate and 3,3'-ethyl-5,5'-methyl-4,4'-diphenylmethane diisocyanate.
3. A polyurethane resin according to Claim 1, wherein a carbodiimide group content possessed by the carbodiimide-modified aromatic diisocyanate is  $1 \times 10^{-2}$  to  $1 \times 10^{-6}$  mole per g of the polyurethane resin.
4. A polyurethane resin according to Claim 1, wherein the carbodiimide-modified aromatic diisocyanate has 1-20 carbodiimide groups.
5. A polyurethane resin obtained from a diol component and a diisocyanate component by an ordinary process, wherein the diisocyanate component comprises:  
at least one kind of unmodified diisocyanate, and  
at least one kind of carbodiimide-modified aliphatic diisocyanate wherein at least one of the two carbons each bonded with an isocyanate group is di- or tri-substituted, and the molar ratio of the unmodified diisocyanate and the carbodiimide-modified aliphatic diisocyanate is 35-0.1:1.
6. A polyurethane resin according to Claim 5, wherein the carbodiimide-modified aliphatic diisocyanate is derived from a diisocyanate selected from the group consisting of 4,4'-dicyclohexylmethane diisocyanate, tetramethylxylene diisocyanate and isophorone diisocyanate.
7. A polyurethane resin according to Claim 5, wherein a carbodiimide group content possessed by the carbodiimide-modified aliphatic diisocyanate is  $1 \times 10^{-2}$  to  $1 \times 10^{-6}$  mole per g of the polyurethane resin..
8. A polyurethane resin according to Claim 5, wherein the carbodiimide-modified aliphatic diisocyanate has 1-20 carbodiimide groups.

#### Patentansprüche

1. Polyurethanharz, hergestellt aus einer Diol-Komponente und einer DiisocyanatKomponente mittels eines herkömmlichen Verfahrens, wobei die DiisocyanatKomponente umfasst:  
mindestens eine Art von unmodifiziertem Diisocyanat, und  
mindestens eine Art von Carbodiimid-modifiziertem aromatischem Diisocyanat, welches, an einer oder beiden der Ortho-Positionen der beiden IsocyanatGruppen, einen aliphatischen, alicyclischen oder aromatischen Substituenten aus ein oder mehreren Kohlenstoffatomen aufweist,  
und wobei das Molverhältnis von unmodifiziertem Diisocyanat zu Carbodiimid-modifiziertem aromatischem Diisocyanat 35-0,1:1 beträgt.
2. Polyurethanharz nach Anspruch 1, wobei das Carbodiimid-modifizierte aromatische Diisocyanat von einem Diisocyanat abgeleitet ist, das gewählt ist aus der Gruppe, bestehend aus 2,4,6-Triisopropylbenzoldiisocyanat, Diethyltolylendiisocyanat und 3,3'-Ethyl-5,5'-methyl-4,4'-diphenylmethandiisocyanat.
3. Polyurethanharz nach Anspruch 1, wobei die Menge an Carbodiimid-Gruppe, die im Carbodiimid-modifizierten aromatischen Diisocyanat enthalten ist,  $1 \times 10^{-2}$  bis  $1 \cdot 10^{-6}$  Mol pro g des Polyurethanharzes beträgt.
4. Polyurethanharz nach Anspruch 1, wobei das Carbodiimid-modifizierte aromatische Diisocyanat 1-20 Carbodiimid-Gruppen aufweist.
5. Polyurethanharz, hergestellt aus einer Diol-Komponente und einer DiisocyanatKomponente mittels eines herkömmlichen Verfahrens, wobei die DiisocyanatKomponente umfasst:

mindestens eine Art von unmodifiziertem Diisocyanat, und

mindestens eine Art von Carbodiimid-modifiziertem aliphatischem Diisocyanat, wobei mindestens einer der beiden Kohlenstoffe, die jeweils mit einer Isocyanatgruppe verbunden sind, di- oder tri-substituiert ist,

und wobei das Molverhältnis von unmodifiziertem Diisocyanats zu Carbodiimid-modifiziertem aromatischem Diisocyanat 35-0,1:1 beträgt.

6. Polyurethanharz nach Anspruch 5, wobei das Carbodiimid-modifizierte aromatische Diisocyanat von einem Diisocyanat abgeleitet ist, das gewählt ist aus der Gruppe, bestehend aus 4,4'-Dicyclohexylmethandiisocyanat, Tetramethylxylendiisocyanat und Isophorondiisocyanat.
7. Polyurethanharz nach Anspruch 5, wobei die Menge an Carbodiimid-Gruppe, die im Carbodiimid-modifizierten aromatischen Diisocyanat enthalten ist,  $1 \times 10^{-2}$  bis  $1 \times 10^{-6}$  Mol pro g des Polyurethanharzes beträgt.
8. Polyurethanharz nach Anspruch 5, wobei das Carbodiimid-modifizierte aromatische Diisocyanat 1-20 Carbodiimid-Gruppen aufweist.

## Revendications

1. Résine polyuréthane obtenue à partir d'un élément diol et d'un élément diisocyanate par un procédé normal, dans laquelle l'élément diisocyanate comprend :

au moins un type de diisocyanate, et  
 au moins un type de diisocyanate modifié par carbodiimide possédant, à un ou aux deux positions ortho des deux groupes isocyanate, un substituant aliphatique, alicyclique ou aromatique ayant un ou plusieurs atomes de carbone,  
 et le rapport molaire entre diisocyanate non modifié et diisocyanate aromatique modifié par carbodiimide est de 35 à 0,1 : 1.

2. Résine polyuréthane selon la revendication 1, dans laquelle le diisocyanate aromatique modifié par carbodiimide est dérivé d'un diisocyanate choisi parmi 2,4,6-triisopropylbenzène diisocyanate, diéthyltolylène diisocyanate et 3,3'-éthyl-5',5-méthyl-4,4'-diphénylméthane diisocyanate.

3. Résine polyuréthane selon la revendication 1, dans laquelle une teneur en groupe carbodiimide du diisocyanate aromatique modifié par carbodiimide est située entre  $1 \times 10^{-2}$  et  $1 \times 10^{-6}$  mole par g de la résine polyuréthane.

4. Résine polyuréthane selon la revendication 1, dans laquelle le diisocyanate aromatique modifié par carbodiimide comporte 1 à 20 groupes carbodiimide.

5. Résine polyuréthane obtenue à partir d'un élément diol et d'un élément diisocyanate au moyen d'un procédé normal, dans laquelle l'élément diisocyanate comprend :

au moins un type de diisocyanate non modifié, et  
 au moins un type de diisocyanate aliphatique modifié par carbodiimide dans lequel au moins l'un des deux atomes de carbone qui sont chacun liés à un groupe isocyanate est di- ou trisubstitué,  
 et le rapport molaire entre diisocyanate non modifiée et diisocyanate aliphatique modifié par carbodiimide est de 35 à 0,1 : 1.

6. Résine polyuréthane selon la revendication 5, dans laquelle le diisocyanate aliphatique modifié par carbodiimide est dérivé d'un diisocyanate choisi parmi 4,4'-dicyclohexylméthane diisocyanate, tétraméthylxylène diisocyanate et isophorone diisocyanate.

7. Résine polyuréthane selon la revendication 5, dans laquelle une teneur en groupe carbodiimide du diisocyanate aliphatique modifié par carbodiimide se situe entre  $1 \times 10^{-2}$  et  $1 \times 10^{-6}$  mole par g de la résine polyuréthane.

8. Résine polyuréthane selon la revendication 5, dans laquelle le diisocyanate aliphatique modifié par carbodiimide

EP 0 799 843 B1

comporte 1 à 20 groupes carbodiimide.

5

10

15

20

25

30

35

40

45

50

55